

Aq. volatile organic solvent free primer compsn. - comprises dispersion of non-ionic, particulate epoxy resins, solid, particulate curing agent and opt. solid particulate elastomer toughener

Patent Assignee: CYTEC TECHNOLOGY CORP

Inventors: SWEET D E

Patent Family

Patent Number	Kind	Date	Application Number	Kind	Date	Week	Type
WO 9406876	A1	19940331	WO 93US8547	A	19930910	199414	B
EP 660861	A1	19950705	EP 93921482	A	19930910	199531	
			WO 93US8547	A	19930910		
US 5461090	A	19951024	US 92944570	A	19920914	199548	
			US 93130229	A	19931001		
JP 8501341	W	19960213	WO 93US8547	A	19930910	199643	
			JP 94508183	A	19930910		
US 5576061	A	19961119	US 92944570	A	19920914	199701	
			US 93130229	A	19931001		
			US 95441490	A	19950515		
EP 660861	B1	19970514	EP 93921482	A	19930910	199724	
			WO 93US8547	A	19930910		
DE 69310754	E	19970619	DE 610754	A	19930910	199730	
			EP 93921482	A	19930910		
			WO 93US8547	A	19930910		
US 5641818	A	19970624	US 92944570	A	19920914	199731	
			US 93130229	A	19931001		
			US 95441487	A	19950515		
ES 2102059	T3	19970716	EP 93921482	A	19930910	199735	

Priority Applications (Number Kind Date): US 92944570 A (19920914); US 93130229 A (19931001); US 95441490 A (19950515); US 95441487 A (19950515)

Cited Patents: AU 436109; DE 2622410; EP 170075 ; EP 60581 ; FR 2519639; WO 8402711

Patent Details

Patent	Kind	Language	Page	Main IPC	Filing Notes
WO 9406876	A1	E	29	D	
Designated States (National): CA JP					
Designated States (Regional): AT BE CH DE DK ES FR GB GR IE IT LU MC NL PT SE					
EP 660861	A1	E		D	Based on patent WO 9406876
Designated States (Regional): AT BE DE DK ES FR GB IE IT NL SE					
US 5461090	A		8	D	Cont of application US 92944570
JP 8501341	W		29	D	Based on patent WO 9406876

US 5576061	A		8	D	Cont of application US 92944570
					Div ex application US 93130229
					Div ex patent US 5461090
EP 660861	B1	E	17	D	Based on patent WO 9406876
Designated States (Regional): AT BE DE DK ES FR GB IE IT NL SE					
DE 69310754	E			D	Based on patent EP 660861
					Based on patent WO 9406876
US 5641818	A		8	D	Cont of application US 92944570
					Div ex application US 93130229
					Div ex patent US 5461090
ES 2102059	T3			D	Based on patent EP 660861

Abstract:

WO 9406876 A

A one component volatile organic solvent free primer compsn. comprises an aq. dispersion of: (a) non-ionic particulate epoxy resin(s) of particle size such that 100 % of the resin particles have mean dia(s). less than 30 mm; and (b) a solid, particulate curing agent selected from solid aromatic diamines of particle size such as 100 % of the particles have mean dia(s). less than 30 microns. The amine to epoxy stoichiometry is greater than 0.5, the aq. dispersion is chemically storage stable and the compsn. when cured shows resistance to organic solvents.

Also claimed are: (i) a one component, volatile organic solvent free primer compsn., comprising an aq. dispersion of (a) and (b) and (c) a solid particulate elastomer toughener; (ii) process for adhering a first metal adherend to a second adherend using the above primers; and (iii) prepn. of a composite article comprising a metal article having a layer of crosslinkable resin bonded to it.

USE/ADVANTAGE - The primers are used for promoting bonding of a metal adherend to a second adherend. Useful in the aerospace and transportation sectors. The compsns. are environmentally superior to solvent based primers without loss of physical properties, they are storage stable and show excellent solvent resistance.

Dwg.0/0

EP 660861 B

A one component, substantially volatile organic solvent free primer composition, comprising an aqueous dispersion of: (a) one or more non-ionic, particulate epoxy resins having a particle size such that essentially 100 per cent of said resin particles have mean diameters less than 30 micron; (b) a solid, particulate curing agent selected from the group consisting of solid aromatic diamines having particle sizes such that essentially 100 percent of said curing agent particles have mean diameters less than 30 micron; such that the amine to epoxy stoichiometry ratio is greater than 0.5, wherein said aqueous dispersion is chemically storage stable, and wherein said composition when cured exhibits resistance to organic solvents.

Dwg.0/0

US 5641818 A

A one component, substantially volatile organic solvent free primer composition, comprising an

aqueous dispersion of:

- (a) one or more non-ionic, solid, particulate epoxy resins;
- (b) a solid, particulate curing agent selected from the group consisting of aromatic diamines; and
- (c) a solid, particulate elastomer toughener component selected from the group

consisting of:

(c)i) a solid prereact prepared by reacting an epoxy resin with a liquid elastomer reactive with epoxy groups; and

(c)ii) a different solid, particulate elastomer, wherein said composition is chemically storage stable, and wherein the particles of said dispersion have a particle size such that essentially 100 percent of said particles have mean diameters less than about 30 μ m.

Dwg.0/0

US 5576061 A

A process for adhering a first metal adherend to a second adherend, comprising:

a) applying to the first metal adherend a one component, volatile organic solvent free primer composition, the composition comprising an aqueous dispersion of: (1) one or more non-ionic, particulate epoxy resins having a particle size such that essentially 100 percent of the resin particles have mean diameters less than about 30 μ m; and (2) a solid, particulate curing agent selected from the group consisting of solid aromatic diamines having particle sizes such that essentially 100 percent of the curing agent particles have mean diameters less than about 30 μ m; such that the amine to epoxy stoichiometry ratio is greater than 0.5, where the aqueous dispersion is chemically storage stable, and where the composition when cured exhibits resistance to organic solvents in an amount such that when cured, a primer coating of from about 0.02 to about 1.0 mils thickness is obtained;

b) curing the primer composition;

c) positioning a thermosettable adhesive between the primed surface of the first metal adherend and the second adherend; and

d) applying heat and pressure such as to cure the thermosettable adhesive.

US 5461090 A

A one component volatile organic solvent free primer compsn. comprises an aq. dispersion of (a) non-ionic, particulate epoxy resin(s) having mean particle dia. below 30 microns; and (b) a solid particulate curing agent comprising a solid aromatic diamine having mean particle dia below 30 microns. The amine to epoxy stoichiometric ratio is above 0.5. The aq. dispersion is chemically storage stable and the compsn. has organic solvent resistance when cured.

The compsn. opt. further comprises a particulate epoxy resin curing catalyst.

USE/ADVANTAGE - Used to promote bonding of a metal or another material. Good physical properties, storage stability and solvent resistance.

Dwg.0/0

Derwent World Patents Index
© 2003 Derwent Information Ltd. All rights reserved.
Dialog® File Number 351 Accession Number 9838580

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : C09D 163/00, C08G 59/50 C09D 5/00, C08J 3/05 C09J 163/00	A1	(11) International Publication Number: WO 94/06876 (43) International Publication Date: 31 March 1994 (31.03.94)
(21) International Application Number: PCT/US93/08547 (22) International Filing Date: 10 September 1993 (10.09.93) (30) Priority data: 07/944,570 14 September 1992 (14.09.92) US (71) Applicant: CYTEC TECHNOLOGY CORP. [US/US]; 5 Garret Mountain Plaza, West Paterson, NJ 07424 (US). (72) Inventor: SWEET, David, Eugene ; 379 Sanford, Irvine, CA 92715 (US). (74) Agent: LERMAN, Bart, E.; CYTEC, 1937 West Main Street. P.O. Box 60, Stamford, CT 06904-0060 (US).		(81) Designated States: CA, JP, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>
(54) Title: AQUEOUS VOC-FREE EPOXY PRIMER COMPOSITIONS (57) Abstract Aqueous primer compositions containing substantially no volatile organic solvents, suitable for promoting the bonding of a metal adherend to a second adherend, are prepared by dispersing one or more solid epoxy resins and a solid curing agent into water such that the particle sizes of the solids are less than 30 µm. The primer compositions are environmentally superior to solvent based primers without loss of physical properties, are storage stable, and exhibit excellent solvent resistance.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	MR	Mauritania
AU	Australia	GA	Gabon	MW	Malawi
BB	Barbados	GB	United Kingdom	NE	Niger
BE	Belgium	GN	Guinea	NL	Netherlands
BF	Burkina Faso	GR	Greece	NO	Norway
BG	Bulgaria	HU	Hungary	NZ	New Zealand
BJ	Benin	IE	Ireland	PL	Poland
BR	Brazil	IT	Italy	PT	Portugal
BY	Belarus	JP	Japan	RO	Romania
CA	Canada	KP	Democratic People's Republic of Korea	RU	Russian Federation
CF	Central African Republic	KR	Republic of Korea	SD	Sudan
CG	Congo	KZ	Kazakhstan	SE	Sweden
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovak Republic
CM	Cameroon	LU	Luxembourg	SN	Senegal
CN	China	LV	Latvia	TD	Chad
CS	Czechoslovakia	MC	Monaco	TG	Togo
CZ	Czech Republic	MG	Madagascar	UA	Ukraine
DE	Germany	ML	Mali	US	United States of America
DK	Denmark	MN	Mongolia	UZ	Uzbekistan
ES	Spain			VN	Viet Nam
FI	Finland				

AQUEOUS VOC-FREE EPOXY PRIMER COMPOSITIONS

Background of the Invention1. Field of the Invention

The subject invention pertains to aqueous primers for metal parts to which composite or metal adherends will be bonded utilizing structural adhesives. More particularly, the subject invention pertains to primers comprising aqueous dispersions of solid epoxy resins and solid curing agents which contain little or no volatile organic solvent.

2. Description of the Related Art

In the current manufacture of composite structures, particularly in the aerospace and transportation sectors, it is frequently necessary to bond a fabricated metallic structure to metal or composite adherends utilizing structural adhesives, generally structural film adhesives, or to laminate one or more plies of thermosetting resin impregnated fibrous reinforcement to the fabricated metal structure. In general, to ensure the greatest level of adhesive strength, the metal surface(s) are scrupulously cleaned of dirt, soil, grease, and metal oxidation products immediately prior to bonding. Unfortunately, this procedure cannot be generally used in a great portion of manufacturing, as the cleaning and bonding operations are often separated significantly in time. During this time period, the metal surface may become reoxidized, lessening the adhesive strength of the bond.

To overcome this difficulty, it has been proposed to prime the cleaned surface. Unfortunately, the primer may not permit the same degree of adhesion to either the metal surface(s) or composite adherends, and thus the resulting joint may not be as strong as that which could be achieved on a freshly prepared surface, although still superior to that which could be obtained from an oxidized surface. The primer must also be receptive to paint as well as adhesives.

Primers have often been prepared from one or two component thermosetting resins diluted to sprayable levels with organic solvents. Liquid epoxy esters were proposed for use in coatings by C.K. Thorstad, "Emulsions - Why and How They are Used", Modern Plastics, July 1959, pp. 83-84, in compositions containing either water or the epoxy ester itself as a vehicle, together with polyvinylacetate, polyacrylic, or poly(butadiene/styrene) lattices. Acid curing agents,

for example dimethyl acid pyrophosphate or boron trifluoride are cited for these applications. However, the use of primers containing large amounts of volatile organic compounds (VOCs) is under increasing scrutiny for both toxicological and environmental reasons.

5 It has been proposed to utilize electrodepositable primers. Such primers contain resin particles bearing a charged group which migrate to an oppositely charged substrate from aqueous solution or dispersion. Such compositions often contain a lower but still undesirable level of VOCs and do not have ideal properties due to the restraints placed on the resin structure.
10 Furthermore, the metal parts must be completely immersed in a tank of primer which impractical for large parts such as aircraft wings or fuselages. To be economical, such baths must be continually monitored and refreshed or must be reprocessed.

 In U.S. Patent 2,872,427 it has been proposed to utilize aqueous
15 emulsions of liquid epoxy resins in textile treating. Additional suggested uses are in paints and enamels. The emulsions contain one or more emulsified liquid epoxy resins dispersed in an aqueous dispersing phase containing an alkali and acid stable non-ionic emulsifying agent and a water-dispersible binding colloid. For those
20 applications where curing agents are also required, the curing agent is dissolved into the epoxy resin prior to dispersion. Such emulsions are storage stable with respect to sedimentation or coagulation, but suffer from the defect that since the epoxy and curing agent are intimately associated, premature curing may take place, particularly when exposed to elevated temperatures during shipment or storage. Shelf life of such emulsions is extremely limited. Furthermore, the protective colloids utilized are
25 not themselves thermally stable, and may cause high temperature performance of the composition to suffer. Finally, such coatings suffer from lack of solvent resistance.

 Raghavon and Lewis in the article "Epoxy Water-Borne Primer: Low-Temp Cure and Zero VOCs", Modern Paint and Coatings, July 1991, evidences the
30 need for water-borne primers without VOCs and suggest use of an aqueous dispersion. However, no details of the composition suitable for such use are given.

U.S. Patent 5,001,173 describes basecoats for metal surfaces which are to be latex primed and painted. The basecoat comprises an aqueous epoxy resin dispersion also containing chromium trioxide and preferably phosphoric acid. The use of aromatic amine or other solid epoxy curing agents is not disclosed. The basecoat is followed by a solvent borne primer containing substantial amounts of polyesters.

In the article "Guidelines to Formulation of Waterborne Epoxy Primers", M.A. Jackson, Polymer Paint Colour Journal 180 (4270) (1990) at pages 608-621 are described two component primer systems containing as one component an epoxy resin dispersion in water and solvent together with various corrosion inhibitors, and as the second component, a water reducible amine catalyst in water. Such formulations require mixing or metering of two separate components and are not storage stable.

In the article "Waterborne Epoxy Dispersions Provide Compliant Alternatives:", R. Buehner et. al., Adhesives Age, December 1991, are described waterborne liquid and solid epoxy resin dispersions cured with dicyandiamide and water soluble 2-methylimidazole catalyst for use as adhesives. However, the shelf life of such dispersions is indicated as only greater than several days.

It would be an advance in the art to prepare a one-component aqueous adhesive primer which contains little or no VOCs; which is storage stable with respect to premature curing for extended periods of time when suitably stored (for example, for a period in excess of 24 weeks when stored at temperatures below 5°C, or for a period in excess of 3 months at ambient temperature); which allows for excellent adhesion of heat-curable resins to the metal substrate, preferably similar to that of a freshly cleaned metal surface; which can be easily and economically be prepared; and whose application to the substrate is practical and economical. These and other objects have been achieved by the use of an aqueous, non-ionic solid epoxy resin dispersion which contain as a distinct phase a solid epoxy curing agent, preferably in the substantial absence of any protective colloid.

Description of the Preferred Embodiments

The epoxy resins of the subject invention are conventional solid epoxy resins having functionalities of about 1.8 or more, preferably 2 or more, containing substantially no ionic or ester groups, as described in Epoxy Resins. Lee and Neville, McGraw-Hill, chapters 1 to 4. Preferred epoxy resins are the optionally chain-extended, solid glycidyl ethers of phenols such as resorcinol and the bisphenols, e.g. bisphenol A, bisphenol F, and the like. Also suitable are the solid glycidyl derivatives of aromatic amines and aminophenols, such as N,N,N',N'-tetraglycidyl-4,4'-diaminodiphenylmethane. Preferred are the solid novolac epoxy resins and solid DGEBA resins. The epoxy resins must be solids themselves, or produce solid compositions when admixed with other epoxies.

Examples of suitable commercial epoxy resins are Epi-Rez® SU-8, a polymeric epoxy resin with an average functionality of about 8, melting point (Durrans) of 82°C, and an epoxy equivalent weight of 215 available from Rhone-Poulenc; DER 669, a high molecular weight solid epoxy resin having a Durrans softening point of 135-155°C and an epoxy equivalent weight of 3500-5500 available from the Dow Chemical Company; Epi-Rez® 522-C, a solid DBEGA epoxy having an epoxy equivalent weight of 550-650 and a Durrans melting point of 75-85°C, available from Rhone-Poulenc; and ECN 1273, 1280, and 1299 orthocresolformaldehyde novolac solid epoxy resins having epoxy functionalities of from 3.8 to 5.4, epoxy equivalent weights of from 225 to 235, and melting points of from 73-99°C, available from Ciba-Geigy. These resins may be supplied in solid form and ground to the correct particle size, or as an aqueous dispersion. For example, ECN-1299 is available as an aqueous dispersion from Ciba-Geigy as ECN-1440, and Epi-Rez® 522C from Rhone-Poulenc as 35201 epoxy dispersion.

Preferably, the epoxy resin dispersed phase comprises from 40 to about 10 percent by weight, and the aqueous continuous phase comprises from 60 to about 90 percent by weight, of the primers. The epoxy resin dispersed phase may comprise a dispersion of more than one epoxy resin as a mixture of distinct particles, or may consist of only one type of particle containing more than one epoxy resin. Thus a flexibilizing epoxy such as the higher molecular weight bisphenol A or bisphenol F epoxies may be blended with a highly temperature resistant epoxy

such as TGMEDA and the mixture cooled, ground, or otherwise dispersed into solid particles of the requisite size. These same epoxy resins might be advantageously dispersed separately without blending.

As indicated above, mixtures of epoxy resins are also suitable. A preferred mixture comprises a solid epoxy resin having a functionality of about 5.5 or less, and a solid epoxy resin having a functionality of about 6 or more. The use of higher functionality epoxy resins, i.e. epoxy resins having a functionality of five or more, in minor amounts is preferred, for examples less than 40 weight percent based on the sum of the weights of all epoxy resins in the composition. The use of such higher functionality epoxy resins in such minor amounts has been unexpectedly found to increase the solvent resistance of the cured primer without lowering adhesive properties substantially. A preferred high functionality epoxy resin is Epi-Rez® SU-8, a polymeric solid epoxy resin having an average functionality of eight. Especially preferred is a mixture of:

- 1) from 30 to 70 weight percent of a solid epoxy resin having a functionality of from about 1.8 to about 4 and an epoxy equivalent weight of from about 400 to about 800;
- 2) from 5 to 20 weight percent of a solid epoxy resin having a functionality of from about 1.8 to about 4 and an epoxy equivalent weight of from about 2000 to about 8000; and
- 3) from 10 to 40 weight percent of a solid epoxy resin having a functionality of about 5 or more and having an epoxy equivalent weight of from about 100 to about 400,

the weight percents totalling 100 percent based on total weight of the epoxy mixture.

The curing agents of the subject invention are preferably substantially water insoluble, and are solids at room temperature. Examples of such curing agents are aromatic amine curing agents such as 4,4'-diaminodiphenylmethane, and in particular, 3,3'- and 4,4'-diaminodiphenylsulfone. Further suitable are 3,3'- and 4,4'-diaminodiphenyloxide, 3,3'- and 4,4'-diaminodiphenyloxide, 3,3'- and 4,4'-diaminodiphenylsulfide, and 3,3'- and 4,4'-diaminodiphenylketone. Most preferred as a curing agent is 4,4'-[1,4-phenylene(1-methylethylidene)]-bis(benzeneamine). Also suitable are the amino and hydroxyl terminated polyarylene oligomers wherein

the repeating phenyl groups are separated by ether, sulfide, carbonyl, sulfone, carbonate, or like groups. Examples of such curing agents are the amino- and hydroxyl-terminated polyarylenesulfones, polyaryleneethersulfones, polyetherketones, polyetheretherketones, and like variants.

5 Other suitable solid diamine curing agents include 2,4-toluenediamine, 1,4-phenylenediamine, 2,2-bis(4-aminophenyl)hexafluoropropane, 2,2-bis(3-amino-4-hydroxyphenyl)hexafluoropropane, 3,4'-diaminodiphenyl oxide, 9,9-bis(4-aminophenyl)fluorene, o-toluidine sulfone, and 4,4'-diaminobenzanilide. Particularly also preferred are 9,10-bis(4-aminophenyl)anthracene, 2,2-bis(4-[3-aminophenoxy]phenyl)sulfone, 2,2-bis(4-[4-aminophenoxy]phenyl)sulfone, 1,4-bis(4-aminophenoxy)biphenyl, bis(4-[4-aminophenoxy]phenyl)ether, 2,2-bis(4-[4-aminophenoxy]phenyl)propane, and 2,2-bis([4-(4-amino-2-trifluorophenoxy)]phenyl)hexafluoropropane. Most preferably, those solid amine curing agents having melting points below 250°F, preferably below 220°F are
10 utilized.

15 Catalysts are generally unnecessary; however, solid, water dispersible catalysts may be added when the particular curing agent is not sufficiently active at the primer bake temperature to effect cure of the primer. The catalyst should be substantially water insoluble, and in particulate form having a particle size such that essentially 100 percent of the particles have mean diameters less than about 30 µm.

20 Volatile organic solvents are undesirable and generally unnecessary. However, it would not depart from the spirit of the invention to employ a most minor portion of such a solvent, i.e. less than 1-2% by weight. Examples of volatile organic solvents which could be added without affecting the function and physical properties of the composition include the low molecular weight glycols and glycol
25 ethers, N-methylpyrrolidone, and similar solvents. By the term "substantially solvent free" is meant that the system contains no volatile organic solvent or such a minor portion that substantially no advantage or difference can be ascertained between the cured physical properties obtained from the completely solventless system and the
30 system containing the minor amount of solvent.

The compositions of the subject invention may include tougheners useful in adhesive systems, for example elastomers, preferably reactive elastomers

such as those containing anhydride, epoxy, amino, or hydroxyl functionality. If the elastomer is a liquid elastomer such as the liquid rubbers sold under the trade name HYCAR, then the elastomer must first be reacted with epoxy resin, either a solid or liquid epoxy, to form a prereact chain-extended elastomer which is a solid. The solid prereact may then be ground or milled to particle sizes less than 30 μm , preferably less than 20 μm , and most preferably such that the majority of particles are in the 2-5 μm range or below. If the elastomer is solid, then it may be ground cryogenically if not supplied in the appropriate size range. Whether formed as a prereact or already in solid form, the elastomer is then dispersed with the remaining ingredients.

The amounts of elastomer are not overly critical, but amounts of from 1 to about 30 weight percent, preferably from about 5 to about 15 weight percent based on total primer solids are adequate. The addition of elastomer to the primer composition, while increasing certain of the cured adhesive's physical properties, particularly peel strength, has the effect of decreasing solvent resistance is required, and thus where solvent resistance for a particular application, the use of elastomers as described herein should be avoided.

The composition may also contain dyes, pigments, leveling agents, additional dispersing agents, thickeners, and the like, although these are generally unnecessary. A benefit of compositions containing dyes or pigments is that surface coverage can be assessed more easily by visual methods. Certain types of pigments may also serve as anti-corrosion additives. Examples of the latter are various salts such as strontium chromate, barium chromate, zinc chromate, and lead chromate, and in particular, the various iron oxides, most preferably the "transparent iron oxides", so-called because of their small particle size.

Suitable corrosion inhibitors are known in the art. Preferred are the metal chromates, for example strontium and barium chromate, and zinc chromate. Amounts of metal chromates of from about 0.3 weight percent to about 5 weight percent are practical. The composition may also contain non-chromate corrosion inhibitors. An preferred example of the latter is SICORIN RZ available from BASF AG, Ludwigshafen, Germany. Amounts of the latter suitable are from about 0.125

weight percent to about 5 weight percent. Further suitable are corrosion inhibitors such as zinc phosphate and zinc molybdate.

The dispersions are generally prepared by first dispersing the solid epoxy resin(s) or blend of solid epoxy resins into the aqueous vehicle. The epoxy resins may be heated to above their melting point or dissolved in a solvent to form a concentrated solution, the solvent being later removed by distillation or stripping. Preferably no solvent is utilized. The resultant liquid epoxy resin or epoxy resin solution is dispersed into water by its slow addition under high shear agitation; by forcing the epoxy through metal plates containing numerous micron sized holes into rapidly agitated water; or by like methods well-known to those of ordinary skill in the art. Finely ground solid epoxy resins may be utilized instead of molten, normally solid epoxy resins. To aid in the maintenance of a stable dispersion, an effective amount of a surfactant may be added. Such surfactants contain both hydrophilic and hydrophobic (lipophilic) portions and include the simple soaps such as the sodium and ammonium salts of long chain fatty acids, long chain fatty alcohol ethoxylates, alkylphenol ethoxylates or block polyoxyalkylene polyethers containing a hydrophobic moiety derived from repeating polyoxypropylene or polyoxybutylene groups or one or more long chain olefin oxide reaction products and a hydrophilic group comprising repeating oxyethylene groups.

Because such surfactants are not generally stable at high temperatures, and because their presence may enhance water absorption by the cured primer, the minimum amount of surfactant should be used. Commercial dispersions of epoxy resins often contain a minor amount of surfactant. If the dispersion of epoxy coagulates or coalesces, then addition of measured amounts of surfactant to freshly prepared dispersions or to the aqueous phase preparatory to formation of the dispersion can be used to assess the stability of the dispersion. Most preferably, the dispersion will be stable with regards to sedimentation of the epoxy resin dispersed phase. However, in the context of the subject invention, the term "stable" refers to a dispersion where the epoxy resin particles do not coalesce or coagulate, but remain substantially in distinct particles. If such particles sediment upon storage, they may be easily redispersed by shaking or moderate agitation. If,

however, the particles coalesce, they will be incapable of redispersion without high shear mixing for prolonged periods of time.

To avoid the necessity of dispersing the epoxy resins, commercially available dispersions may be utilized to supply certain of the epoxy resin ingredients.

5 Such dispersions are available from a number of manufacturers, for example from Ciba-Geigy as ECN-1400, a dispersion of epoxy novolac ECN 1299 in water; and Epi-Rez® 35201, a dispersion of a solid DGEBA epoxy resin, CMD W50-3519, an elastomer modified epoxy dispersion, and W55-5003, an SU-3 epoxy dispersion, all available from Rhone-Poulenc. In any case, the particle size of the epoxy resin
10 should be such that essentially 100 percent of the particles have sizes less than 30 μm , preferably less than 20 μm . Best results are obtained with essentially 100 percent of the particles being less than 16 μm , with 90 percent less than 2 μm . Such particles sizes may be obtained by the methods previously described, or by traditional grinding methods such as jet milling, ball milling, or sand milling.

15 Following dispersion of the epoxy resin(s) into the aqueous phase, the curing agent is added. The curing agent is first reduced to a fine particle size, preferably of less than 0.1 μm to about 30 μm , and more preferably from about 1 μm to about 10 μm , in diameter, whereby essentially 100 percent of the particles have mean diameters less than 30 μm . In general, the finer the particle size, the
20 more dispersible the primer will be, and also the more resistant to sedimentation. In addition, small particle sizes such as these have been unexpectedly found to increase solvent resistance of the cured primer. The particle sizes herein are measured with a Brinkmann Particle Size Analyzer based on probability number density.

25 The curing agent may be also reduced to small particle size by known methods, including spray drying, solution precipitation, ball milling, sand milling, air jet milling, and the like. The fine curing agent particles are added to the epoxy emulsion or dispersion and agitated until a uniform mixture is obtained. Following or preceding addition of the curing agent, other additives such as dyes, pigments,
30 corrosion preventatives, and the like, may be added.

Amine to epoxy stoichiometry may range from about 0.5 to about 1.5. However, if maximum solvent resistance is desired, the amine/epoxy ratio should

be from about 0.8 to about 1.5, preferably about 1.0. Solvent resistance is assessed by wiping with methylethylketone solvent twenty times after the primer is cured. Acceptable solvent resistance is shown when following 20 wipes there is negligible visible damage to the film, i.e. the film is still intact and of substantially the same thickness as initially. There should be little or not loss of polymer from the cured film.

The low VOC primer is applied by traditional methods, for example by air driven or airless spray guns, by high volume low pressure spray guns, and the like, for example a Binks model 66 spray gun. Following drying, the finish is baked at a temperatures sufficient to the cure the coating. Nominal curing temperatures range from 100-200°C, preferably 100-175°C, and most preferably at about 115-125°C. Cure time is dependent upon cure temperature and can be, for example from about 0.5 to about 4 hours. Preferably, the primer is cured at about 120°C for one hour. Nominal cured coating thickness is from 0.02 to 1.0 mils (0.5 to 25.4 μm), preferably from 0.05 to 0.5 mils (1.3 to 12.7 μm), and especially from 0.05 to 0.25 mils (1.3 to 6.4 μm). Surprisingly, even though the epoxy resin and curing agent are in distinct phases, the coatings produced are of exceptionally high quality.

Once the primer has been applied to a substrate, such as a metal adherend, a second adherend, such as a second metal substrate or a composite substrate, can be adhered to the so-primed substrate in a normal manner by positioning a thermosettable adhesive between the primed surface of the substrate and the second adherend, then applying heat and pressure such as to cure thermosettable adhesive. Thermosettable adhesives suitable for a particular application, as well as the suitability for such application and curing conditions thereof, are well-known to those of ordinary skill in the art.

In a similar manner, composite metal/resin articles can be formed by applying a crosslinkable resin onto the primed surface of metal substrate, then curing the crosslinkable resin. A wide variety of well-known crosslinkable resins may be suitable for forming such composite metal/resin articles. Such crosslinkable resins may be in the form, for example, of a paint or laminate, and may further incorporate a wide variety of additives well-known for a particular application. As one such additive may be mentioned fibrous reinforcements.

The invention will now be illustrated by reference to the following examples.

Example 1

A primer formulation was prepared by dispersing the following ingredients, in parts by weight.

5	Epi-Rez® SU-8 epoxy resin ¹	1.85
	DER 669 epoxy resin ²	2.10
	Cabosik®	0.3
	Epi-Rez® 35201 ³	17.0
	Epon HPT Curing Agent 1061-M ⁴	2.1
10	Pigment	1.0
	Corrosion Inhibitor	1.6
	Water	70.0

15 ¹Product of Rhone-Poulenc, a solid epoxy resin having a functionality of c.a. 8, and a EEW of 215.

²Product of Dow Chemical Co., a bisphenol A based solid epoxy having an EEW of 350°-5500 and a softening point of from 135-155°C.

20 ³A water dispersion of a solid bisphenol A epoxy resin having a viscosity of 12000 cps at 25°C and 60 percent solids, available form Rhone-Poulenc.

⁴4,4'-[1,4-phenylene(1-methylethylidene)]-bis(benzeneamine), available from Shell Chemical Co.

Examples 2-4

A primer formulation was prepared by dispersing the following ingredients, ground to particle sizes such that 100% were below 20 μ m, into water.

		<u>Example 2</u>	<u>Example 3</u>	<u>Example 4</u>
5	RD 90-027	100.0	100.0	100.0
	DER 669/Hycar CTBN	--	--	5.5
	Paraloid 2691	6.0	6.0	6.0
	Pigment	4.0	4.2	8.0
				nominal
10	4,4'-diaminodiphenylsulfone	2.0	5.0	--
	HPT 1061-M	--	--	5.5
	Cabosil M5	1.0	1.0	--
	Curezol C17Z ¹	0.5	--	--
	Water (deionized)	100.0	108.0	139.0
15	¹ 2-heptadecyl-1H-imidazole			

Primers were coated onto metal adherends and showed acceptable performance when tested for Bell peel strength and lap shear strength. All showed acceptable corrosion resistance. However, solvent resistance (MEK) was found to be in need of improvement.

Example 5

A primer composition was made as in examples 1-4, having the following compositions in weight percent.

5	Epirez® SU-8	4.0
	DER 669	2.2
	WD-35201	9.0 (based on resin solids)
	HPT-1061	2.6
	Cabosil M5	0.35
10	SrCrO ₄	0.24
	BaCrO ₄	1.4
	Deionized Water	80.0

This formulation, when cured, showed excellent solvent resistance.

Examples 6-7

Similar to Examples 1-5 primers were prepared having the following compositions.

		<u>Example 6</u>	<u>Example 7</u>
5	WD 35201	14.78	14.78
	DER 669	2.16	2.16
	SU-8	3.71	3.71
	HPT 1061-M	2.67	2.67
	Cabosil M5	0.36	0.36
10	SrCrO ₄	0.23	--
	BaCrO ₄	1.35	--
	Paleotol® Yellow	0.29	--
	Heilogen® green	--	0.29
	SICORIN RZ	--	1.58
15	Deionized Water	74.45	74.45

These formulations were used to prime 2024 T3 aluminum adherends and cured at 250°F (121°C) for one hour, following which the adherends were bonded with a variety of structural adhesives, cured and tested as indicated in Tables 1 to 5. In these tables, "Non-Chromated" refers to the primer of Example 7 while "chromated" refers to the primer of Example 6. "No Prime" indicates that no primer was used. "Solvent" indicates that a solvent based primer was utilized for comparison purposes.

The tables indicate that use of the aqueous primer compositions of the subject invention perform their function well, promoting bonding between adherends with the aid of structural adhesives which compare well to bond properties obtained from freshly prepared metal surfaces. The bond properties also exceed those obtained from solvent based primers, particularly with respect to 250°F (121°C) wet lap shear strength.

TABLE I - LAP SHEAR PERFORMANCE

LAP SHEAR DATA lbs/in ² (x10 ⁷ N/m ²)	-67°F (-55°C)	RT	250°F (121°C)	75°F (24°C) WET (2)	350°F (177°C)	420°F (216°C)
ADHESIVE/ PRIMER						
METLBOND® ¹ NO PRIME	6254 (4.31)	5797 (4.00)	3638 (2.51)	5798 (4.00)		
METLBOND® NON- CHROMATED	6154 (4.24)	6679 (4.60)	3471 (2.39)	5747 (3.96)		
METLBOND® CHROMATED	6453 (4.45)	6842 (4.72)	3558 (2.45)	5934 (4.09)		
FM300 ² NO PRIME	5465 (3.77)	5207 (3.59)	3734 (2.57)	5747 (3.96)		
FM300 CHROMATED	4709 (3.25)	5727 (3.95)	3472 (2.39)	6023 (4.15)		
FM400 ² NO PRIME	4123 (2.84)	4267 (2.94)		3397 (2.34)	2987 (2.06)	2136 (1.47)
FM400 CHROMATED	4171 (2.86)	4046 (2.79)		3377 (2.33)	2131 (1.47)	1776 (1.22)

(1) Indicates 30-Day Exposure Requirement. Lap shear specimens had average bond line thicknesses measuring 0.005 inches (0.13 mm). Cross Head test rate was 0.05 inches/minute (1.3 mm/min). All primed specimens were sprayed with one box coated to yield a cured primer thickness of 0.15 to 0.2 mils (3.6 to 5.1 μm).

(2) Accelerated exposures (72-hour water boil) were run to give an indication of wet primer performance.

¹Metlbond® 1146 structural adhesive available from BASF Structural Materials, Inc.

²FM 300 and FM 400 structural adhesives available from American Cyanamid Co.

TABLE 2 - BELL PEEL PERFORMANCE

BELL PEEL in-lbs/in (m-N/m)		-67° F (-55°C)	RT	250°F (121°C)
5	ADHESIVE/PRIMER			
	METLBOND® 1146 NO PRIME	28 (124.5)	62 (275.8)	59 (262.4)
	METLBOND® 1146 NON- CHROMATED	34 (151.2)	57 (253.5)	58 (258.0)
10	METLBOND® 1146 CHROMATED	32 (142.3)	58 (258.0)	57 (253.5)
	FM 300 NO PRIME	29 (129.0)	41 (182.4)	40 (177.9)
	FM 300 CHROMATED	25 (111.2)	41 (182.4)	39 (173.5)
	FM 400 NO PRIME	8.0 (35.6)	8.0 (35.6)	NOT REQUIRED
	FM 400 NON-CHROMATED	16 (71.2)	17 (75.6)	NOT REQUIRED
15	FM 400 CHROMATED	14 (62.3)	14 (62.3)	NOT REQUIRED
	AF163 NO PRIME	75 (333.6)	79 (351.4)	NOT REQUIRED
	AF163 CHROMATED	67 (298.0)	80 (355.8)	NOT REQUIRED

Bell peel specimens for FM 300 and FM 400 had bond line thicknesses of 0.010 inches (0.254 mm). Metlbond® 1146 adhesive bond line thickness was measured at 0.006 inches (0.152 mm). Cross Head test speed was 6 inches/minute (152 mm/minute). All primed specimens were sprayed with one box coat to yield a cured primer thickness of 0.15 to 0.2 mils (3.6 to 5.1 μm).

AF163 is from 3M Company.

TABLE 3
TEST RESULTS
SOLVENT BASED PRIMER TO WATER BASED PRIMER

5

PRIMER	BELL PEEL in-lb/in (m-N/m)			LAP SHEAR lbs/in ² (x10 ⁷ N/m ²)	
	-67°F (-55°C)	75°F (29°C)	250°F (121°C)	75°F (29°C)	250°F (121°C) WET
NO PRIME	35 (155.7)	58 (258.0)	55 (244.6)	6470 (4.46)	2141 (1.48)
SOLVENT	--	63 (280.2)	47 (209.1)	6320 (4.36)	470 (0.32)
CHROMATED	32 (142.3)	63 (280.2)	52 (231.3)	6330 (4.36)	2130 (1.47)

10

PRIMER RESULTS SPRAY COATED AT OR NEAR 0.1 MIL (2.5 μm), BONDED WITH METLBOND® 1146 ADHESIVE.

TABLE 4
PEEL VERSUS CHROMATED PRIMER THICKNESS

	SHEAR lbs/in ² ($\times 10^7$ N/m ²)		PEEL in-lb/in (m-N/m)	
	75°F (29°C)	250°F (121°C)	75°F (29°)	-67° (-55°C)
NO PRIME (CONTROL)	6700 (4.62)	2300 (1.56)	81 (360.3)	35 (155.7)
5 1 BOX COAT (0.05 MILS) (1.27 μ m)	7000 (4.83)	2800 (1.93)	84 (373.6)	40 (177.9)
2 BOX COATS (0.1 MILS) (2.54 μ m)	6600 (4.55)	3000 (2.07)	82 (364.7)	41 (182.4)
10 4 BOX COATS (0.2 MILS) (5.08 μ m)	6400 (4.41)	2900 (2.00)	82 (364.7)	42 (186.8)
6 BOX COATS (0.25 MILS) (6.35 μ m)	6900 (4.76)	3000 (2.07)	78 (346.9)	36 (160.1)

(19% Solids, Binks Model 66 Spray Gun).

15 2024 T3 Al, FPL, etch, PAA.

Primer Cured at 250°F (121°C), 60 Min.

Bonded with Metlbönd® 1146 Adhesive, Cured at 350°F (172 °C), 90 min., 35 psi
(2.41×10^5 N/m²)

TABLE 5
CHROMATED PRIMER WITH 250°F OR 350°F ADHESIVES

BELL PEEL in-lb/in (m-N/m)				LAP SHEAR lbs/in ² (x10 ⁷ N/m ²)			
5	350°F CURE ¹ (177°C)	-67°F (-55°C)	RT	250°F (121°C)	-67°F (-55°C)	RT	250°F (121°C) 250°F (121°C) WET
	NO PRIME	34 (151.2)	73 (324.7)	64 (284.7)	6190 (4.27)	6373 (4.39)	3310 (2.28) 970 (0.67)
10	CHRO- MATED	29 (129.0)	74 (329.2)	61 (271.3)	6290 (4.34)	6505 (4.49)	2640 (1.82) 1060 (0.73)
	250°F CURE ¹ (121°C)						
15	NO PRIME	24 (106.8)	61 (271.3)	55 (244.6)	6405 (4.42)	6535 (4.51)	3475 (2.40) 2130 (1.47)
	CHRO- MATED	32 (142.3)	63 (280.2)	52 (231.3)	5745 (3.96)	6330 (4.36)	3380 (2.33) 2130 (1.47)
20	250°F CURE (121°C)						
	AF 163 NO PRIME	75 (333.6)	79 (351.4)		7175 (4.95)	6745 (4.65)	180°F (82°C) 3415 (2.35) 180°F (82°C) WET 2040 (1.41)
25	CHRO- MATED	67 (298.0)	80 (355.8)		6895 (4.75)	6545 (4.51)	3445 (2.38) 1983 (1.37)

2024T3 A1, FPL etch, PAA. Primed at 0.2 mils (5.08 μ m), cure 60 min. 250°F (121°C).

Bonded and Cured at 250°F (121°C) or 350°F (177°C) as indicated, 90 min., 35 psi (2.41 x 10⁵ N/m²).

¹Metlbond® 1146 adhesive.

I claim:

1. A one component, substantially volatile organic solvent free primer composition, comprising an aqueous dispersion of:

a) one or more non-ionic, particulate epoxy resins having a particle size such that essentially 100 percent of said resin particles have mean diameters less than about 30 μm ;

b) a solid, particulate curing agent selected from the group consisting of solid aromatic diamines having particle sizes such that essentially 100 percent of said curing agent particles have mean diameters less than about 30 μm ;

such that the amine to epoxy stoichiometry ratio is greater than 0.5, wherein said aqueous dispersion is chemically storage stable, and wherein said composition when cured exhibits resistance to organic solvents.

2. The primer composition of Claim 1 wherein said epoxy resin is a mixture of epoxy resins comprising:

- a)i) a solid epoxy resin having a functionality of about 5.5 or less, and
- a)ii) a solid epoxy resin having a functionality of 6 or more.

3. The primer composition of Claim 1 wherein said aromatic amine curing agent is selected from the group consisting of 4,4'-diaminodiphenylsulfone, 3,3'-diaminodiphenylsulfone, 4,4'-diaminodiphenylketone, and 4,4'-[1,4-phenylene(1-methylethylidene)]bis(benzeneamine).

4. The primer composition of Claim 2 wherein said aromatic amine curing agent is selected from the group consisting of 4,4'-diaminodiphenylsulfone, 3,3'-diaminodiphenylsulfone, 4,4'-diaminodiphenylketone, and 4,4'-[1,4-phenylene(1-methylethylidene)]bis(benzeneamine).

5. The primer composition of Claim 1 wherein the dispersed phase of said dispersion comprises from 40 to about 10 percent by weight of said dispersion and the aqueous continuous phase comprises from 60 to about 90 percent by weight of said dispersion, and wherein the epoxy resin comprises, based on the total weight of the epoxy resin:

- 1) from 30 to 70 weight percent of a solid epoxy resin having a functionality of from 1.8 to about 4 and an epoxy equivalent weight of from 400 to 800;
- 2) from 5 to about 20 weight percent of a solid epoxy resin having a functionality of from 1.8 to about 4 and an epoxy equivalent weight of from about 2000 to about 8000; and;
- 3) from 10 to about 40 weight percent of a solid epoxy resin having a functionality of 5 or more and having an epoxy equivalent weight of from about 100 to about 400,

said weight percents totalling 100 percent based on total weight of the epoxy component.

6. The primer composition of Claim 3 wherein the dispersed phase of said dispersion comprises from 40 to about 10 percent by weight of said dispersion and the aqueous continuous phase comprises from 60 to about 90 percent by weight of said dispersion, and wherein the epoxy resin comprises, based on the total weight of the epoxy resin:

- 1). from 30 to about 70 weight percent of a solid epoxy resin having a functionality of from 1.8 to about 4 and an epoxy equivalent weight of from 400 to 800;
- 2). from 5 to about 20 weight percent of a solid epoxy resin having a functionality of from 1.8 to about 4 and an epoxy equivalent weight of from about 2000 to about 8000; and;
- 3). from 10 to about 40 percent of a solid epoxy resin having a functionality of 5 or more and having an epoxy equivalent weight of from about 100 to about 400,

said weight percents totalling 100 percent based on total weight of the epoxy component.

7. The primer compositions of Claim 1, further comprising an effective amount of a catalyst which promotes the cure of epoxy resins, said catalyst being a solid catalyst in particulate form having a particle size such that essentially 100 percent of said particles have mean diameters less than about 30 μ m.

8. The primer composition of claim 1 wherein said epoxy resins contain substantially no ester groups.

9. A one component, substantially volatile organic solvent free primer composition, comprising an aqueous dispersion of:

- a) one or more non-ionic, solid, particulate epoxy resins;
- b) a solid, particulate curing agent selected from the group consisting of aromatic diamines;
- c) a solid, particulate elastomer toughener component selected from the group consisting of:
 - c)i) a solid prereact prepared by reacting an epoxy resin with a liquid elastomer reactive with epoxy groups;
 - c)ii) a solid, particulate elastomer other than the prereact of c)i),

wherein said composition is chemically storage stable, and wherein the particles of said dispersion have a particle size such that essentially 100 percent of said particles have mean diameters less than about 30 μ m.

10. The primer composition of Claim 9 wherein said epoxy resin is a mixture of epoxy resins comprising:

- a)i) a solid epoxy resin having a functionality of about 5.5 or less, and
- a)ii) a solid epoxy resin having a functionality of 6 or more.

11. The primer composition of Claim 9 wherein said aromatic diamine curing agent is selected from the group consisting of 4,4'-diaminodiphenylsulfone, 3,3'-diaminodiphenylsulfone, 4,4'-diaminodiphenylketone, and 4,4'-[1,4-phenylene(1-methylethylidene)]bis(benzeneamine).

5

12. The primer composition of Claim 10 wherein said aromatic diamine curing agent is selected from the group consisting of 4,4'-diaminodiphenylketone, and 4,4'-[1,4-phenylene(1-methylethylidene)]bis(benzeneamine).

10

13. The primer composition of Claim 9 wherein the dispersed phase of said dispersion comprises from 40 to about 10 percent by weight of said dispersion and the aqueous continuous phase comprises from 60 to about 90 percent by weight of said dispersion, and wherein the epoxy resin comprises, based on the total weight of the epoxy resin:

15

1) from 30 to 70 weight percent of a solid epoxy resin having a functionality of from 1.8 to about 4 and an epoxy equivalent weight of from 400 to 800;

2) from 5 to about 20 weight percent of a solid epoxy resin having a functionality of from 1.8 to about 4 and an epoxy equivalent weight of from about 2000 to about 8000; and;

20

3) from 10 to about 40 weight percent of a solid epoxy resin having a functionality of 5 or more and having an epoxy equivalent weight of from about 100 to about 400,

said weight percents totalling 100 percent based on total weight of the epoxy component.

25

14. The primer composition of Claim 10 wherein the dispersed phase of said dispersion comprises from 40 to about 10 percent by weight of said dispersion and the aqueous continuous phase comprises from 60 to about 90 percent by weight of said dispersion, and wherein the epoxy resin comprises, based on the total weight of the epoxy resin:

30

1). from 30 to about 70 weight percent of a solid epoxy resin having a

functionality of from 1.8 to about 4 and an epoxy equivalent weight of from 400 to 800;

2). from 5 to about 20 weight percent of a solid epoxy resin having a functionality of from 1.8 to about 4 and an epoxy equivalent weight of from about 2000 to about 8000; and;

3). from 10 to about 40 percent of a solid epoxy resin having a functionality of 5 or more and having an epoxy equivalent weight of from about 100 to about 400,

said weight percents totalling 100 percent based on total weight of the epoxy component.

15. The primer composition of Claim 9, further comprising an effective amount of a catalyst which promotes the cure of epoxy resins, said catalyst being a solid catalyst in particulate form having a particle size such that essentially 100 percent of said particles have mean diameters less than about 30 μ m.

16. The primer composition of claim 9 wherein said epoxy resins contain substantially no ester groups.

17. The primer composition of claim 9 wherein the amount of elastomer is from 1 to 30 weight percent based on total primer solids.

18. A process for adhering a first metal adherend to a second adherend, comprising:

- a) applying to said first metal adherend the primer composition of any one of Claims 1-17 in an amount such that when cured, a primer coating of from 0.02 to 1.0 mils (0.5 to 25.4 μ m) thickness is obtained;
- b) curing said primer composition;
- c) positioning a thermosettable adhesive between the primed surface of said first metal adherend and said second adherend;
- d) applying heat and pressure such as to cure said thermosettable adhesive.

19. The process of claim 18 wherein the primer is applied to said first metal adherend in an amount such that when cured, a primer coating of from 0.05 to 0.5 mils (1.3 to 12.7 μm) thickness is obtained.

5 20. A process for preparing a composite article comprising a metal article to which is bonded a layer of crosslinkable resin, comprising:

- 10 a) applying to the surface of said metal article which is to be bonded to said crosslinkable resin the primer composition of any one of Claims 1-17 in an amount such that when cured, a primer coating having a thickness of from 0.02 to about 1.0 mils (0.5 to 25.4 μm) thickness is obtained;
- b) curing said primer composition;
- c) applying a crosslinkable resin to said metal article, and
- 15 d) curing said crosslinkable resin.

21. The process of Claim 20 wherein said crosslinkable resin is a thermosettable resin.

20 22. The process of Claim 21 wherein said thermosettable resin further incorporates fibrous reinforcement.

23. The process of Claim 20 wherein said crosslinkable resin is a paint.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 93/08547

A. CLASSIFICATION OF SUBJECT MATTER

IPC 5 C09D163/00 C08G59/50 C09D5/00 C08J3/05 C09J163/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 5 C09D C08G C08J C09J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP,A,0 060 581 (AKZO) 22 September 1982 see example 1 see page 3, line 18 ---	1
A	WO,A,84 02711 (BASF) 19 July 1984 see claim 1; example 1 ---	1
A	DE,A,26 22 410 (INVENTA AG) 25 November 1976 see claims 1,4 see example 1 ---	1,7
A	AU,A,436 109 (UNISEARCH LTD) 14 June 1973 see claims 1,6-8 ---	1,7
A	EP,A,0 170 075 (BASF) 5 February 1986 see claims 1-4 ---	1,3,4, 11,12
	--- -/-	

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

& document member of the same patent family

Date of the actual completion of the international search

25 November 1993

Date of mailing of the international search report

17. 12. 93

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

O'Sullivan, T

INTERNATIONAL SEARCH REPORT

Intern. Application No

PCT/US 93/08547

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	FR,A,2 519 639 (TOHO BESLON CO. LTD.) 18 July 1983 see claim 1 -----	7

INTERNATIONAL SEARCH REPORT

Information on patent family members

Intern. Application No

PCT/US 93/08547

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-0060581	22-09-82	CA-A- 1205231	27-05-86
		JP-B- 2022773	21-05-90
		JP-A- 57162762	06-10-82
		US-A- 4555412	26-11-85
WO-A-8402711	19-07-84	DE-A- 3300561	12-07-84
		EP-A- 0132261	30-01-85
DE-A-2622410	25-11-76	CH-A- 614972	28-12-79
		AT-A, B 361176	25-02-81
		AT-B- 352407	25-09-79
		FR-A, B 2324694	15-04-77
		SE-A- 7605684	21-11-76
AU-A-436109	23-05-73	AU-A- 3967472	14-06-73
EP-A-0170075	05-02-86	DE-A- 3424700	06-02-86
		JP-A- 61034021	18-02-86
		US-A- 4607069	19-08-86
		US-E- RE32628	22-03-88
FR-A-2519639	18-07-83	JP-B- 1057130	04-12-89
		JP-C- 1569133	10-07-90
		JP-A- 58120639	18-07-83
		BE-A- 895590	02-05-83
		CH-A- 656627	15-07-86
		DE-A, C 3301119	25-08-83
		GB-A, B 2115423	07-09-83
		NL-A- 8300120	01-08-83
		US-A- 4482660	13-11-84